

China GB Standard	National Standard Unified Digital Code	ASTM/ ASME	UNS Code	EN
06Cr19Ni10	S30408	304	S30400	1.4301
022Cr19Ni10	S30403	304L	S30403	1.4307
07Cr19Ni10	S30409	304H	S30409	1.4948
06Cr19Ni10N	S30458	304N	S30451	1.4315
06Cr17Ni12Mo2	S31608	316	S31600	1.4401
022Cr17Ni12Mo2	S31603	316L	S31603	1.4404
06Cr17Ni12Mo2Ti	S31668	316Ti	S31635	1.4571
06Cr18Ni11Ti	S32168	321	S32100	1.4541
07Cr19Ni11Ti	S32169	321H	S32109	1.4941
06Cr25Ni20	S31008	310S	S31008	1.4845
06Cr19Ni13Mo3	S31708	317	S31700	1.4449
022Cr19Ni13Mo3	S31703	317L	S31703	1.4438
06Cr18Ni11Nb	S34778	347	S34700	1.4550
07Cr18Ni11Nb	S34779	347H	S34709	1.4912
022Cr22Ni5Mo3N	S22253	S31803	S31803	1.4462
022Cr23Ni5Mo3N	S22053	S32205	S32205	1.4462
022Cr25Ni7Mo4N	S25073	S32750	S32750	1.4410
022Cr25Ni7Mo4WCuN	S27603	S32760	S32760	1.4501
015Cr20Ni18Mo6CuN	S31252	254SMO	S31254	1.4547
015Cr21Ni26Mo5Cu2	S31782	904L	N08904	1.4539
Ni68Cu28Fe	--	Monel 400	N04400	2.4360
1Cr15Ni75Fe8	NS3102	Inconel 600	N06600	2.4816
0Cr20Ni65Mo10Nb4	NS3306	Inconel 625	N06625	2.4856
0Cr30Ni60Fe10	NS3105	Inconel 690	N06690	2.4642
0Cr20Ni32AlTi	NS1101	Incoloy 800	N08800	1.4876
1Cr20Ni32AlTi	NS1102	Incoloy 800H	N08810	1.4958
0Cr25Ni35AlTi	NS1103	Incoloy 800HT	N08811	1.4959
0Cr21Ni42Mo3Cu2Ti	NS1402	Incoloy 825	N08825	2.4858
00Cr15Ni60Mo16W5Fe5	NS3304	C276	N10276	2.4819
0Cr20Ni35Mo3Cu3Nb	NS1403	Alloy 20	N08020	2.4660

Stainless Steel Grade Chart

[More information](#)